



Big bags 1000 kg



Bags 25 kg



Pellet length 7 - 12 mm



Swelling capacity 50 - 60%

TECHNICAL DATA



ikolit® 300 M is a modified Mikolit® 300. Magnetite, a strong magnetic, ferrous mineral is added to the raw material. This ensures that introduced clay layers are detectable with simple equipment. The swelling and the sealing of the Mikolit® 300 is only slightly influenced by the additive. After the spaces between the grains have been filled up, a wide degree of swelling capacity remains, which means that, in case of damaging, the clay layer will repair itself. The introduced clay layer is not water saturated and therefore it is a rather fixed clay layer. Quality 300M has sublime sinking quality's, due to the fact that the product is free of dust, it has a strongly slowed down start of swelling, it has favorable grain dimensions and due to the additive it has increased density. The chosen raw materials make the product very little adhesive to casings, which makes the product very arranged for drillings with temporary casings. It is recommended to bring in some course sand at the level where there is a connection between the Mikolit®

300 M and gravel. Also in salty water enough swelling remains to insure a good sealing.

Product name:	Mikolit® 300M					
Pellet color:	Black/grey					
Pellet size:	$\emptyset \pm 8$ mm, length 7 – 12 mm					
Package:	Bags 25 kg/big bags 1000 kg					
Sinking speed in water:	21 m/min					
Density water saturated:	2,0 t/m³					
Bulk density:	1,3 t/m³					
Start of swelling:	15 min					
Swelling capacity:	50 – 60% 1)					
Permeability:	< 10 ⁻¹¹ m/s					
Swelling pressure:	6-8 kN/m ²					
γ-ray:	80 – 100 API					

Distributed by:

Quantity needed (kg/m)

		Bore-hole (mm)								(mm) 🕨
	300M	100	125	150	200	250	300	400	500	600
Tube/Casing (mm)	0	10	16	23	41	63	91	162	254	365
	50	8	13	20	38	61	89	160	251	363
	100		6	13	30	53	81	152	243	355
	125			7	25	48	75	146	238	349
	160				15	37	65	136	228	339
	200					23	51	122	213	324
	250						28	99	190	302
	315							63	153	264
	400								91	203
	500									112

Mikolit®-products are produced by:



Engelenkampstraat 71 • Postbus 78 • NL-6130 AM Sittard Telefoon: +31 (0) 46 4 526 662 Fax: +31 (0) 46 4 513 055

F-mail: info@terratech.nl

¹⁾ Free swelling in goblet glass in dem. water, additional to pore volume.